

Care instructions

Wooden floors, impregnated
wax care acc. to DIN 18356



brief instructions

procedure	product	remarks
<i>primary care</i>	LOBA® ParkettWax	-
<i>maintenance</i>	LOBA® WaxCleaner	aqueous wipe care
	LOBA® ParkettWax	care basing on waxes
<i>stripping</i>	LOBA® WaxRemover	-

general remarks

Wood

Wood is a natural product. It changes its dimensions and adapts permanently to the rooms' relative humidity.

During the heating period relative humidity decreases significantly causing the wood inevitably to react and to emit its own humidity - it shrinks. The longer and stronger rooms are heated, the drier the air will be and thus broader joints will form. Usually the broadest joints are to be expected at the end of the heating period. At the end of summer the joints are commonly least broad or completely closed.

To counteract the joints formation, relative humidity values below 45% are to be avoided. This can be achieved by using special air humidifiers. Conditions of 20 °C and 50% r.h. have proved useful for both the wood's preservation and human well-being.

Underfloor heatings

It must be taken care that multi-circuit systems of underfloor heatings in connected rooms are operated equally. A surface temperature of 29 °C must not be exceeded. In contrast to central heated rooms an enforced joint formation is to be expected.

Wood oils

By using floor oils, the wood will be impregnated and protected against intruding water. This treatment will leave the wood-pores unsealed. To protect them against soiling, a subsequent treatment with floor-waxes should be carried out. Floor-waxes will close the pores, add a soft gloss to the floor and produce an additional protection against water. Freshly impregnated floors are not to be used during the first 24 hours. Careful usage of the floor during the first few days will improve its lifetime. Full stressability will be achieved after 8-14 days.

According to the stress, oils are subjected to a natural wear. To counteract this effect, a regular caring procedure according to DIN 18356 is necessary. On severe damages in the surface caused by normal stress, the floor can be partially renovated.

Cleaning and caring of impregnated parquet

Only dry cleaning during the first week after varnishing (broom, mop, vacuum cleaner). Do not inhibit the drying process by placing carpets. Cleaning and caring-procedures can be easily performed by using floor-waxes and aqueous cleaners. They can be used 8-14 days at the earliest after impregnating.

First cleaning

Use LOBA® Cleaner.

primary care

Apply LOBA® ParkettWax thinly and polish immediately after drying.

maintenance

Cleaning

Dry-clean your floor by using mop, broom or vacuum cleaner. Dirt and dust have the same effect as sanding paper and thus are to be removed instantly. Damp-mop your floor if required (e.g. in case of heavy stains, spots, etc.) using LOBA® WaxCleaner.

revised

30.01.2008

form revised

02.08.2005/GR

printed

30.01.2008

page 1 of 2

Care instructions

Wooden floors, impregnated wax care acc. to DIN 18356



The floor will be cleaned and cared simultaneously.

Caring

Maintenance caring can be (also partially in heavily stressed areas) carried out by renewed application of LOBA® ParkettWax. Fatty spots, heel marks and other heavy stains will hereby be removed. Polish after drying.

Repair of slight damages

By using the floor slight damages appear to the base oil. They can be - even partially - worked over with LOBA® ParkettOil. To do so remove any soil and wax residues from the damaged places using LOBA® WaxRemover and a green pad. After drying work over with LOBA® ParkettOil. The floor can be treated with a floor wax again after drying over night.

Repair of heavy damages

Heavy damages are - even partially - repaired by applying the appropriate base oil once more. To do so remove any soil and wax residues from the damaged places using LOBA® WaxRemover and a green pad. After drying the wood is to be treated with the base oil. The floor can be treated with a floor wax again after drying over night.

stripping

Manual or mechanical stripping procedures are only necessary if the floor shows heavy stains which can not be removed by maintenance cleaning. We recommend the usage of LOBA® WaxRemover.

notes

Stripping procedures should be carried out as seldom as possible.

This bulletin can only be considered as recommendation without obligation. On account of the wide variety of conditions in practice, this information is not binding and does not warrant a contractual legal relationship or accessory obligations.